

Material: ASTM A 29 1022

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1022 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.230	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Aluminium	Al %	0.020 max.		
Boron	B %	0.0005 - 0.003		
Copper	Cu %	0.200 max.		
Niobium	Nb %	0.025 max.		
Silicon	Si %	0.100 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	379 min.
-	-	-	Yield Strength in Mpa	230 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	40 - 47
-	-	-	Hardness in HB	121 - 137
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10220	UNS	USA	Bars, Wire Rods and Tubing
1022	SAE	USA	Steel, Bar and Forging
1022	AISI	USA	Steel, Bar and Forging
A 1040 1022	ASTM	USA	Steel
A 108 Grade 1022	ASTM	USA	Steel and Bar
A 510 1022	ASTM	USA	Wire Rod and Round Wire
A 513 Grade 1022	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com