

Material: ASTM A 29 1037

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1037 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.380	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0005 - 0.003		
Silicon	Si %	0.100 max.		
Copper	Cu %	0.200 max.		
Aluminium	Al %	0.020 max.		
Niobium	Nb %	0.015 max.		
Vanadium	V %	0.020 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	510 - 570
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 - 40
-	-	-	Hardness in HB	143 - 167
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10370	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1037	SAE	USA	Steel
1037	AISI	USA	Steel and Bar
A 1040 1037	ASTM	USA	Steel
A 510 1037	ASTM	USA	Wire Rod and Round Wire
A 576 10L37	ASTM	USA	Steel and Bar
A 830 1037	ASTM	USA	Plate

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com