

Material: ASTM A 29 1053

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1053 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0005 - 0.003		
Copper	Cu %	0.200 max.		
Silicon	Si %	0.100 max.		
Aluminium	Al %	0.020 max.		
Niobium	Nb %	0.015 max.		
Vanadium	V %	0.020 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	770 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	220 - 260
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10530	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1053	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1053	AISI	USA	Steel and Bar
A 1040 1053	ASTM	USA	Steel
A 510 1053	ASTM	USA	Wire Rod, Round Rod and Steel
A 576 10L53	ASTM	USA	Steel and Bar
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com