

Material: ASTM A 29 1132

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1132 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment
Carbon	C %	0.270 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering
Manganese	Mn %	1.350 - 1.650	
Phosphorus	P %	0.040 max.	
Sulphur	S %	0.080 - 0.130	
Silicon	Si %	0.100 max.	
Aluminium	Al %	0.020 max.	
Niobium	Nb %	0.015 Max.	
Vanadium	V %	0.020 max.	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
Mechanical Properties			
			Tensile Strength in Mpa
			550 - 760
			Yield Strength in Mpa
			310 - 620
			Elongation in %
			12 - 23
			Reduction of Area in %
			35 - 40
			Hardness in HB
			164 - 217
			Impact in Joule
			-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G11320	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1132	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1132	AISI	USA	Steel and Bar
A 1040 1132	ASTM	USA	Steel
A 510 1132	ASTM	USA	Wire Rod, Round Wire and Steel
A 519 1132	ASTM	USA	Steel and Tubing
A 576 11L32	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India