

Material: ASTM A 29 M1010

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 M1010 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 - 0.140	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.250 - 0.600		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Niobium	Nb %	0.025 max.		
Aluminium	Al %	0.020 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 275 - 655 Yield Strength in Mpa 170 min. Elongation in % 5 min. Reduction of Area in % 40 - 50 Hardness in HB 95 - 105 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10100	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1010	SAE	USA	Sheet and Tubing
1010	AISI	USA	Tubing
A 1040 1010	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 108 Grade 1010	ASTM	USA	Bar and Sheet
A 29 1010	ASTM	USA	Bar
A 510 1010	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com