

# Material: ASTM A 29 M1012

## Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A 29 M1012 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bar

Chemical Composition		
Carbon	C %	0.090 - 0.160
Manganese	Mn %	0.250 - 0.600
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Aluminium	Al %	0.020 max.
Niobium	Nb %	0.025 max.
Vanadium	V %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	330 - 370
Yield Strength in Mpa	180 min.
Elongation in %	19 min.
Reduction of Area in %	40 - 50
Hardness in HB	95 - 105
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10120	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1012	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1012	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 1040 1012	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1012	ASTM	USA	Bar
A 510 1012	ASTM	USA	Wire Rod
A 512 Grade 1012	ASTM	USA	Tubing

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India