

Material: ASTM A 352 Grade LC2-1

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 352 Grade LC2-1 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.550 - 0.750		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	1.350 - 1.850		
Molybdenum	Mo %	0.300 - 0.600		
Nickel	Ni %	2.500 - 3.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	725 - 895
-	-	-	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17NiCrMo13-6	BS	British	Plate, Tubes and Forging
G17NiCrMo13-6	ISO	International	Casting
1.6781	ISO	International	Casting
A 352 J42215	ASTM	USA	Casting
G 17 NiCrMo13 6	ONORM	Australia	Casting
G 17 NiCrMo13 6	NBN	Belgium	Casting
G 17 NiCrMo13 6	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com