

Material: ASTM A 479 S44700

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 479 S44700 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.010 max.
Silicon	Si %	0.200 max.
Manganese	Mn %	0.300 max.
Phosphorus	P %	0.025 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	28.000 - 30.000
Molybdenum	Mo %	3.500 - 4.200
Nickel	Ni %	0.150 max.
Nitrogen	N %	0.020 max.
Copper	Cu %	0.150 max.
C + N	C% + N%	0.025 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	380 min.
Elongation in %	20 min.
Reduction of Area in %	40 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44700	ASTM	USA	Steel, Plate, Sheet and Strip
S44700	UNS	USA	Steel
A176 S44700	ASTM	USA	Steel, Sheet, Plate and Strip
A276 S44700	ASTM	USA	Steel, Bar and Shapes
A493 S44700	ASTM	USA	Steel, Wire, Rod and Forging
A580 S44700	ASTM	USA	Steel and Pipe
SA-276 S44700	ASME	USA	Steel, Bar and Shapes

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India