

Material: ASTM A 576 1117

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 576 1117 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.140 - 0.200	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 - 1.300		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.080 - 0.130		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 430 - 480 Yield Strength in Mpa 230 min. Elongation in % 15 min. Reduction of Area in % 40 - 47 Hardness in HB 121 - 248 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G11170	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1117	SAE	USA	Steel, Bar, Forging and Tubing
1117	AISI	USA	Steel and Bar
SUM 31	JIS	Japan	Steel
SA-311 1117 Class A	ASME	USA	Steel and Bar
A 576 11L17	ASTM	USA	Steel and Bar
A 29 1117	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com