

Material: ASTM A 713 G10900

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 713 G10900 Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.850 - 0.980	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 700 - 840 Yield Strength in Mpa 460 min. Elongation in % 10 min. Reduction of Area in % 25 - 40 Hardness in HB 197 - 248 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10900	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1090	SAE	USA	Steel and Wire
1090	AISI	USA	Steel and Wire
A 1040 1090	ASTM	USA	Steel
A 29 1090	ASTM	USA	Steel and Bar
A 510 1090	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 10L90	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com