

## Material: ASTM A 743 Grade CY-40

### Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** ASTM A 743 Grade CY-40 Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	3.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	14.000 - 17.000		
Iron	Fe %	11.000 max.		
Nickel	Ni %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	195 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
3444 Grade 20	IS	India	Casting
C-NiCr15Fe	AFNOR NF	France	Pump, Valve and Fitting
NC16Fe11-M	AFNOR NF	France	Pump, Valve and Fitting
NC6040	AFNOR NF	France	Pump, Valve and Fitting
10774 Grade 12	IS	India	Casting
NiCrFC	JIS	Japan	Casting
A 744 Grade CY-40	ASTM	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)