

Material: ASTM A 789 S39274

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 789 S39274 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	2.500 - 3.500		
Nitrogen	N %	0.240 - 0.320		
Copper	Cu %	0.200 - 0.800		
Tungsten	W %	1.500 - 2.500	Mechanical Properties	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	800 min.
			Yield Strength in Mpa	550 min.
			Elongation in %	15 min.
			Reduction of Area in %	-
			Hardness in HB	310 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S39274	ASTM	USA	Steel, Plate, Sheet and Strip
S39274	UNS	USA	Steel
A790 S39274	ASTM	USA	Steel and Pipe
A815 S39274	ASTM	USA	Steel and Pipe
A959 S39274	ASTM	USA	Steel and Pipe
A988 S39274	ASTM	USA	Steel
SA-789 UNS S39274	ASME	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com