

Material: ASTM A 830 1552

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Plate and Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 830 1552 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Plate and Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: *Plate and Steel*

Chemical Composition			Heat Treatment
Carbon	C %	0.470 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering
Manganese	Mn %	1.200 - 1.500	
Phosphorus	P %	0.030 max.	
Sulphur	S %	0.030 max.	
Silicon	Si %	0.150 - 0.350	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
Mechanical Properties			
Tensile Strength in Mpa			680 - 740
Yield Strength in Mpa			410 min.
Elongation in %			10 min.
Reduction of Area in %			30 - 40
Hardness in HB			193 - 217
Impact in Joule			-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15520	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1552	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1552	AISI	USA	Steel and Bar
A 29 1552	ASTM	USA	Steel and Bar
A 510 1552	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 G15520	ASTM	USA	Plate and Steel
A 866 1552	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com