

Material: ASTM A 830 G10600

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 830 G10600 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.550 - 0.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.040 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	300 - 330
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	45 - 55
-	-	-	Hardness in HB	86 - 95
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10060	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
10060	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1006	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 1040 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 510 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 830 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com