

Material: ASTM A 959 S31277

Standard Specification for Seamless and Heavily Cold Worked Austenitic Stainless Steel Pipes

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM A 959 S31277 Seamless and Heavily Cold Worked Austenitic Stainless Steel Pipes

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	3.000 max.		
Chromium	Cr %	20.500 - 23.000		
Molybdenum	Mo %	6.500 - 8.000		
Copper	Cu %	0.500 - 1.500		
Nitrogen	N %	0.300 - 0.400		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Nickel	Ni %	26.000 - 28.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	1620 min.
-	-	-	Yield Strength in Mpa	1345 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Incoloy 27-7MO	Gravity	India	Sheet, Plate, Bar and Wire
A 213 S31277	ASTM	USA	Tube
A 240 S31277	ASTM	USA	Plate, Sheet and Strip
A 249 S31277	ASTM	USA	Tube
A 312 S31277	ASTM	USA	Pipe
A 580 S31277	ASTM	USA	Wire
SA-213 S31277	ASME	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com