

Material: ASTM A176 Type XM-27

Standard Specification for Stainless and Heat-Resisting Chromium Steel Plate, Sheet and Strip

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A176 Type XM-27 Stainless and Heat-Resisting Chromium Steel Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.400 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	25.000 - 27.500		
Molybdenum	Mo %	0.750 - 1.500		
Nickel	Ni %	0.500 max.		
Niobium	Nb %	0.050 - 0.200		
Nitrogen	N %	0.015 max.		
			Mechanical Properties	
Ni+Cu	Ni% + Cu%	0.500 max.	Tensile Strength in Mpa	450 min.
Copper	Cu %	0.200 max.	Yield Strength in Mpa	275 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	45 min.
-	-	-	Hardness in HB	190 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-731 TPXM-27	ASME	USA	Casting
A240 Type XM-27	ASTM	USA	Plate, Sheet and Strip
A276 XM-27	ASTM	USA	Bar and Shapes
S44627	UNS	USA	Plate, Sheet and Strip
SM-27	SAE	USA	Plate, Sheet and Strip
SA-276 XM-27	ASME	USA	Bar and Shapes
A731 TP XM-27	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com