

Material: ASTM A216 WCC

Standard Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A216 WCC Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.030 max.		
other	%	1.000 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	485 - 655
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA 216 WCC	ASME	USA	Casting
A660 WCC	ASTM	USA	Fusion Welding, Bending and Forming
SA 660 WCC	ASME	USA	Centrifugal Casting
J02503	UNS	USA	Casting
A216 WCB	ASTM	USA	Casting
1.0619	EN	European Union	Casting
1.0619	DIN	Germany	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com