

Material: ASTM A240 UNS S30500

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.	Solution Annealing	
Silicon	Si %	0.750 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	10.500 - 13.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	183 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CF8	ASTM	USA	Casting
304	AISI	USA	Bar, Wire, Strip, Plate, Sheet and Forging
1.4308	DIN	Germany	Casting
1.4301	EN	European Union	Forging
304 S 11	BS	British	Bright Bars, Hot Rolled and Cold Rolled Coil
SUS 304	JIS	Japan	Hot Rolled Equal Leg Angles
08CH18N10	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com