

Material: ASTM A240 UNS S32050

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	20.000 - 23.000		
Molybdenum	Mo %	6.000 - 6.800		
Nitrogen	N %	0.210 - 0.320	Mechanical Properties	
Copper	Cu %	0.400 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	675 min.
			Yield Strength in Mpa	330 min.
			Elongation in %	40 min.
			Reduction of Area in %	-
			Hardness in BHN	250 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A213 S32050	ASTM	USA	Tubes for Superheaters and Heat Exchanges
A240 S32050	ASTM	USA	Plate, Sheet and Strip
A 959 S32050	ASTM	USA	Plate, Sheet and Strip
A358 S32050	ASTM	USA	Pipes
A249 S32050	ASTM	USA	Tubes for Superheaters and Heat Exchanges
S32050	UNS	USA	Plate, Sheet and Strip
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com