

Material: ASTM A240 UNS S33400

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	19.000 - 21.000		
Aluminium	Al %	0.150 - 0.600		
Titanium	Ti %	0.150 - 0.600		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S22400	UNS	USA	Steel
A959 Type 334	ASTM	USA	Steel
X8CrNiAlTi20-20	DIN	Germany	Steel
1.4847	DIN	Germany	Steel
SA-240 S33400	ASME	USA	Steel
SA-240 Type 334	ASME	USA	Steel
A240 S33400	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com