

## Material: ASTM A240 UNS S40500

### Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.500		
Nickel	Ni %	0.600 max.		
Aluminium	Al %	0.100 - 0.300		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa   415 min. Yield Strength in Mpa   170 min. Elongation in %   20 min. Reduction of Area in %   - Hardness in BHN   179 max. Impact in Joule   -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S40500	UNS	USA	Steel
405	AISI	USA	Steel
405	AMS	USA	Sheet, Bar, Wire, Shape and Forging
405	AS	Australia	Steel, Sheet, Plate and Strip
405	SAE	USA	Sheet, Bar, Wire, Shape and Forging
STS 405	KS	Korea	Steel and Wire
SUS 405	JIS	Japan	Steel, Plate and Sheet

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)