

Material: ASTM A240 UNS S43600

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment			
Carbon	C %	0.120 max.	Annealing or Hardening + Tempering			
Silicon	Si %	1.000 max.				
Manganese	Mn %	1.000 max.				
Phosphorus	P %	0.040 max.				
Sulphur	S %	0.030 max.				
Chromium	Cr %	16.000 - 18.000				
Molybdenum	Mo %	0.750 - 1.250				
Niobium	Nb %	5*C - 0.800 max.				
Iron	Fe %	Balance				
-	-	-				
-	-	-	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.		
-	-	-	Yield Strength in Mpa	240 min.		
-	-	-	Elongation in %	22 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in BHN	-		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S43600	UNS	USA	Steel
436 S 20	BS	British	Steel and Wire
51436	SAE	USA	Steel
A959 Type 436	ASTM	USA	Steel
STS 436L	KS	Korea	Steel, Sheet, Plate and Strip
SUS 436L	JIS	Japan	Steel, Sheet, Plate and Strip
A651 TP 434	ASTM	USA	Steel and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com