

Material: ASTM A297 Grade HC

Standard Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A297/ A297M Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.500 max.	As - Cast	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	26.000 - 30.000		
Nickel	Ni %	4.000 max.		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	380 min.
			Yield Strength in Mpa	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J92605	UNS	USA	Casting
452 C 11	BS	British	Casting
1.4823	DIN	Germany	Casting
G X 35 Cr 28	UNI	Italy	Casting
40 CrNiSi 25-4	MSZ	Hungary	Casting
G X 40 CrNiSi 27-4	DIN	Germany	Casting
A297 Grade HD	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com