

Material: ASTM A297 Grade HE

Standard Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A297/ A297M Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.500	As - Cast	
Silicon	Si %	2.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	26.000 - 30.000		
Nickel	Ni %	8.000 - 11.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	585 min.
			Yield Strength in Mpa	275 min.
			Elongation in %	9 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J93403	UNS	USA	Casting
SCH 18	JIS	Japan	Casting
J94013	UNS	USA	Casting
A608 Grade HE 35	ASTM	USA	Casting
J93403	UNS	USA	Casting
SCH 17	JIS	Japan	Casting
A608 Grade HE 35	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com