

Material: ASTM A351 CF3MN

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A351 / 351M Castings, Austenitic, for Pressure-Containing Parts

Application: Intended for Valves, Pumps, General Engineering, Automobile and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	17.000 - 21.000		
Nickel	Ni %	9.000 - 13.000		
Molybdenum	Mo %	2.000 - 3.000		
Nitrogen	N %	0.100 - 0.200		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	515 min.
			Yield Strength in Mpa	255 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CF3MN	ASTM	USA	Casting
316L	AISI	USA	Bar, Wire, Strip, Plate, Sheet and Forging
1.4404	DIN	Germany	Cold Rolled, Strips, Slit Coils and Sheets
1.4404	EN	European Union	Rod, Bars, Wire and Forging
316 S 11	BS	British	Bright Bars, Hot Rolled and Cold Rolled Coil
SUS 316L	JIS	Japan	Hot Rolled Equal Leg Angles
03CH17N14M3	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com