

Material: ASTM A351 CF8C

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A351 / 351M Castings, Austenitic, for Pressure-Containing Parts

Application: Intended for Valves, Pumps, General Engineering, Automobile and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	18.000 - 21.000		
Nickel	Ni %	9.000 - 12.000		
Molybdenum	Mo %	0.500 max.		
Niobium	Nb %	C(8) - 1.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CF8C	ASTM	USA	Casting
A 744 CF8C	ASTM	USA	Casting
GX5CrNiNb 19-11	DIN	Germany	Casting
1.4552	EN	European Union	Casting
347 C 17	BS	British	Casting
SCS 21	JIS	Japan	Casting
SA 351 CF8C	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com