

Material: ASTM A351 CK20

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A351 / 351M Castings, Austenitic, for Pressure-Containing Parts

Application: Intended for Valves, Pumps, General Engineering, Automobile and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.200	Solution Annealing	
Silicon	Si %	1.750 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	23.000 - 27.000		
Nickel	Ni %	19.000 - 22.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	195 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CK20	ASTM	USA	Casting
SA-351 Grade CK20	ASME	USA	Casting
1.4843	DIN	Germany	Round and Flat Wire
SCS 18	JIS	Japan	Centrifugal Cast Steel Pipes
Ch25N20	GOST	Russia	Precision Alloys
H 23 N 18	PN	Poland	Heat Resisting Steel
T 25 NiCr 250	STAS	Romania	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com