

Material: ASTM A352 CA6NM

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A352 / A352M Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	760 - 930
			Yield Strength in Mpa	550 min.
			Elongation in %	15 min.
			Reduction of Area in %	35 min.
			Hardness in BHN	-
			Impact in Joule	27 min. @ -73°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ASTM A743 CA6NM	ASTM	USA	Casting
A356 CA6NM	ASTM	USA	Casting
A487 CA6NM	ASTM	USA	Casting
SA-352 Grade CA6NM	ASME	USA	Casting
SA-487 Grade CA6NMA	ASME	USA	Casting
SA-487 Grade CA6NMB	ASME	USA	Casting
SA-487 Class CA6NM	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com