

# Material: ASTM A352 Grade LC1

## Standard Specification for Ferritic and Martensitic Steel Castings for Pressure Containing Parts

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A352 Grade LC1 Ferritic and Martensitic Steel Castings for Pressure Containing Parts

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Molybdenum	Mo %	0.450 - 0.650
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Normalizing or Annealing or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	450 - 620
Yield Strength in Mpa	240 min.
Elongation in %	24 min.
Reduction of Area in %	35 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA217 WC1	ASME	USA	Casting
G20 Mo 5	EN	European Union	Casting
SCPH 11	JIS	Japan	Casting
J12524	UNS	USA	Casting
G 20 MO5	DIN	Germany	Casting
G 20 MO5	UNI	Italy	Casting
A217 Grade WC1	ASTM	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India