

Material: ASTM A487 12(B)

Standard Specification for Steel Castings Suitable for Pressure Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A487 / AA87M Steel Castings Suitable for Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.200	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 - 0.900		
Nickel	Ni %	0.600 - 1.000		
Molybdenum	Mo %	0.900 - 1.200		
Copper	Cu %	0.500 max.		
Vanadium	V %	0.030 max.		
Tungsten	W %	0.100 max.		
Other	Ot %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	725 - 895
Yield Strength in Mpa	585 min.
Elongation in %	17 min.
Reduction of Area in %	35 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J22000	UNS	USA	Casting
A487 12A	ASTM	USA	Casting
A217 WC5	ASTM	USA	Casting
SA-487 12A	ASME	USA	Casting
SA-487 12B	ASME	USA	Casting
SA-217 WC5	ASME	USA	Casting
A487 Grade 6N	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com