

Material: ASTM A487 2(C)

Standard Specification for Steel Castings Suitable for Pressure Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A487 / AA87M Steel Castings Suitable for Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.300 max.
Silicon	Si %	0.800 max.
Manganese	Mn %	1.000 - 1.400
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Chromium	Cr %	0.350 max.
Nickel	Ni %	0.500 max.
Molybdenum	Mo %	0.100 - 0.300
Copper	Cu %	0.500 max.
Vanadium	V %	0.030 max.
Tungsten	W %	0.100 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment	
Annealing or Normalising or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	450 min.
Elongation in %	22 min.
Reduction of Area in %	40 min.
Hardness in HB	235 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13005	UNS	USA	Casting
1.0457	EN	European Union	Pipes
1.0484	DIN	Germany	Pipes
13030	CSN	Czech Republic	Steel
20 MB5	AFNOR NF	France	Cold Rolled and Strips
230 - 45000	JIS	Japan	Casting
3	AS	Australia	Hot Rolled Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com