

Material: ASTM A487 9(E)

Standard Specification for Steel Castings Suitable for Pressure Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A487 / AA87M Steel Castings Suitable for Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.330	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.600 - 1.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.750 - 1.100		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.150 - 0.300		
Tungsten	W %	0.100 max.		
Vanadium	V %	0.030 max.		
			Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	795 min.
Other	Ot %	1.000 max.	Yield Strength in Mpa	655 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13345	UNS	USA	Casting
A487 9A	ASTM	USA	Casting
A487 9B	ASTM	USA	Casting
A487 9C	ASTM	USA	Casting
A487 9D	ASTM	USA	Casting
SA-487 9A	ASME	USA	Casting
SA-487 9B	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com