

Material: ASTM A487 CA15(A)

Standard Specification for Steel Castings Suitable for Pressure Service

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A487 / AA87M Steel Castings Suitable for Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	1.000 max.		
Molybdenum	Mo %	0.500 max.		
Copper	Cu %	0.500 max.		
Vanadium	V %	0.050 max.		
Tungsten	W %	0.100 max.	Mechanical Properties Tensile Strength in Mpa 965 - 1170 Yield Strength in Mpa 760 - 895 max. Elongation in % 10 min. Reduction of Area in % 25 min. Hardness in BHN - Impact in Joule -	
Other	Ot %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A217 CA 15	ASTM	USA	Casting
A487 CA 15B	ASTM	USA	Casting
5351	AMS	USA	Casting
410	AISI	USA	Bar, Wire, Shape and Forging
410 C 21	BS	British	Casting
15Ch13L	GOST	Russia	Casting
385 G X 12 Cr 13	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India