

Material: ASTM A580 S21800

Standard Specification for Austenitic Stainless and Heat Resisting Steel Wire

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A580 S21800 Austenitic Stainless and Heat Resisting Steel Wire

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	Annealed.	
Silicon	Si %	3.500 - 4.500		
Manganese	Mn %	7.000 - 9.000		
Phosphorus	P %	0.060 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Nickel	Ni %	8.000 - 9.000		
Nitrogen	N %	0.080 - 0.180		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 655 min. Yield Strength in Mpa 345 min. Elongation in % 35 min. Reduction of Area in % 55 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CF10MnN	ASTM	USA	Casting
J92972	UNS	USA	Casting
S21800	UNS	USA	Casting
5848	AMS	USA	Bar, Wire, Extrusions, Tube, Ring and Forging
SA-276 S21800	ASME	USA	Bar and Shapes
SA-351 CF10SMnN	ASME	USA	Casting
A351 CF10SMnN	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India