

Material: ASTM A608 Grade HI 35

Standard Specification for Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A608 Grade HI 35 Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.300 - 0.400
Silicon	Si %	0.500 - 2.000
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	26.000 - 30.000
Nickel	Ni %	14.000 - 18.000
Molybdenum	Mo %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As - Cast

Mechanical Properties	
Tensile Strength in Mpa	56 max.
Yield Strength in Mpa	-
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SCH 18	JIS	Japan	Casting
J94013	UNS	USA	Casting
J94003	UNS	USA	Casting
SCH 17	JIS	Japan	Casting
J93413	UNS	USA	Casting
A 608 G HE35	ASTM	USA	Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India