

Material: ASTM A731 29-4

Standard Specification for Castings, Seamless and Ferritic Stainless Steel Pipe

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A731/ A731M Seamless and Ferritic Stainless Steel Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.200 max.		
Manganese	Mn %	0.300 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	28.000 - 30.000		
Molybdenum	Mo %	3.500 - 4.200		
Copper	Cu %	0.150 max.		
Nitrogen	N %	0.020 max.		
Ni+Cu	Ni% + Cu%	0.150 max.		
N+C	N % + C %	0.025 max.	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 415 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-731 29-4	ASME	USA	Casting
S44700	UNS	USA	Plate, Sheet and Strip
A176 S44700	ASTM	USA	Plate, Sheet and Strip
A268 29-4	ASTM	USA	Tube
A493 S44700	ASTM	USA	Forging
A580 S44700	ASTM	USA	Wire
A791 Grade 29-4	ASTM	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com