

Material: ASTM A732 10Q

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.450	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.700 - 0.900		
Nickel	Ni %	1.650 - 2.000		
Molybdenum	Mo %	0.200 - 0.300		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
other	Ot %	1.000 max.	Mechanical Properties Tensile Strength in Mpa 1241 min. Yield Strength in Mpa 1000 min. Elongation in % 5 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
4340	AISI	USA	Forging, Bar, Wire, and Shape
4340	SAE	USA	Bar, Wire, Sheet, Strip and Forging
4340	AMS	USA	Bar and Forging
J24054	UNS	USA	Casting
J13080	UNS	USA	Casting
A487 13B	ASTM	USA	Casting
SA 487 13A	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com