

Material: ASTM A732 15A

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.950 - 1.100
Silicon	Si %	0.200 - 0.800
Manganese	Mn %	0.250 - 0.550
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Chromium	Cr %	1.300 - 1.600
Nickel	Ni %	0.500 max.
Copper	Cu %	0.500 max.
Tungsten	W %	0.100 max.
Other	Ot %	0.600 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Annealing or Normalizing or Hardening + Tempering	
Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRB	100 Max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
52100	AISI	USA	Forging, Bar, Wire, and Shape
52100	SAE	USA	Bar, Wire, Sheet, Strip and Forging
52100	AMS	USA	Bar and Forging
J19166	UNS	USA	Casting
BL3	BS	British	Tool Steel
J19965	UNS	USA	Casting
K19964	UNS	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India