

Material: ASTM A732 2Q

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.250 - 0.350
Silicon	Si %	0.200 - 1.000
Manganese	Mn %	0.700 - 1.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Chromium	Cr %	0.350 max.
Nickel	Ni %	0.500 max.
Copper	Cu %	0.500 max.
Tungsten	W %	0.100 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Annealing or Normalizing or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	586 min.
Yield Strength in Mpa	414 min.
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1030	AISI	USA	Forging, Bar, Wire, and Shape
J03011	UNS	USA	Casting
1.1811	WN	Germany	Casting
161-480	BS	British	Casting
1.5408	EN	European Union	Rod, Bars, Wire and Extrusion
SCPL1	JIS	Japan	Casting
A732 2A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India