

Material: ASTM A743 CG12

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.	Solution Annealing	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	20.000 - 23.000		
Nickel	Ni %	10.000 - 13.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	485 min.
			Yield Strength in Mpa	195 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J93001	UNS	USA	Casting
G X 5 CrNi 22-10	DIN	Germany	Casting
1.4947	DIN	Germany	Casting
3444 Grade 2	IS	India	Casting
A743 J93001	ASTM	USA	Casting
CG-12	NBR	Brazil	Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com