

Material: ASTM A743 CK3MCuN

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.500 - 20.500		
Nickel	Ni %	17.500 - 19.500		
Molybdenum	Mo %	6.000 - 7.000		
Copper	Cu %	0.500 - 1.000		
Nitrogen	N %	0.180 - 0.240		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	550 min.
			Yield Strength in Mpa	260 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 CK3MCuN	ASTM	USA	Casting
SA-351 CKMCuN	ASME	USA	Casting
Z 4 CND 19.13 M	AFNOR NF	France	Casting
317 C 12	BS	British	Casting
422940	CSN	Czech Republic	Casting
J92810	UNS	USA	Casting
J93254	UNS	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com