

Material: ASTM A743 CN3M

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.000 - 22.000		
Nickel	Ni %	23.000 - 27.000		
Molybdenum	Mo %	4.500 - 5.500		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	435 min
			Yield Strength in Mpa	170 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 CN3M	UNS	USA	Casting
1.4585	DIN	Germany	Casting
J94651	UNS	USA	Casting
Ao X 10 CrNiMoCuNb 18-18	MSZ	Hungary	Casting
G X 7 CrNiMoCuNb 18-18	DIN	Germany	Casting
A351 CN3MN	ASTM	USA	Casting
1.4588	ISO	International	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com