

Material: ASTM A747 Grade CB7Cu-2 (H900)

Standard Specification for Steel Castings, Stainless, Precipitation Hardening

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A747 / A747M Steel Castings, Stainless, Precipitation Hardening

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.700 max.	Mechanical Properties	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.	Tensile Strength in Mpa or Hardening	170 min.
Chromium	Cr %	14.000 - 15.500	Yield Strength in Mpa	1000 min.
Nickel	Ni %	4.500 - 5.500	Elongation in %	5 min.
Copper	Cu %	2.500 - 3.200	Reduction of Area in %	-
Niobium	Nb %	0.150 - 0.350	Hardness in BHN	375 min.
Nitrogen	N %	0.050 max.	Impact in Joule	-
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J92110	UNS	USA	Casting
J92130	UNS	USA	Casting
SA-747 CB7Cu-2	ASME	USA	Casting
5356	AMS	USA	Casting
AMS 5346	SAE	USA	Casting
5400	AMS	USA	Casting
5357	AMS	USA	Casting

