

Material: ASTM A791 Grade 29-4-2

Standard Specification for Unannealed Ferritic Stainless Steel Tubing

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A791 Grade 29-4-2 Unannealed Ferritic Stainless Steel Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.200 max.		
Manganese	Mn %	0.300 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	28.000 - 30.000		
Molybdenum	Mo %	3.500 - 4.200		
Nickel	Ni %	2.000 - 2.500		
Nitrogen	N %	0.020 max.		
Cu+Ni	Cu% + Ni%	2.500 max.		
Copper	Cu %	0.150 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	415 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	541 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S44800	UNS	USA	Plate, Sheet and Strip
A268 29-4-2	ASTM	USA	Plate, Sheet and Strip
A497 S44800	ASTM	USA	Plate, Bar and Forging
A511 29-4-2	ASTM	USA	Tube
SA-731 29-4-2	ASME	USA	Casting
SA-240 Type 29-4-2	ASME	USA	Plate, Sheet and Strip
A731 29-4-2	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com