

Material: ASTM A890 6A

Standard Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A890 / A890M Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.500 - 8.500		
Molybdenum	Mo %	3.000 - 4.000		
Copper	Cu %	0.500 - 1.000		
Nitrogen	N %	0.200 - 0.300		
Tungsten	W %	0.500 - 1.000	Mechanical Properties	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	690 min.
			Yield Strength in Mpa	450 min.
			Elongation in %	25 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A995 6A	ASTM	USA	Casting
J93380	UNS	USA	Casting
A240 S32205	ASTM	USA	Plate, Sheet and Strip
A276 S32205	ASTM	USA	Bar and Shape
A988 S32205	ASTM	USA	Casting
J92205	UNS	USA	Casting
Z3CNUD26.5M	AFNOR NF	France	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com