

Material: ASTM A890 CD3MWN

Standard Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A890 / A890M Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 - 3.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	26.000- 28.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	2.000 - 3.500		
Copper	Cu %	1.000 max.		
Nitrogen	N %	0.300 - 0.400		
Tungsten	W %	3.000 - 4.000		
Barium	Ba %	0.0002 - 0.0100		
Boron	Bo %	0.001 - 0.010		
Ce + La	Ce % + La %	0.005 - 0.030		
Iron	Fe %	Balance		

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	485 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A995 7A	ASTM	USA	Casting
J93379	UNS	USA	Casting
27Cr7NiMoWN	ASTM	USA	Casting
7A	ASTM	USA	Casting
A995 CD3MWN	ASTM	USA	Casting
A995 J93379	ASTM	USA	Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com