

Material: ASTM A890 CD4MCuN

Standard Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A890 / A890M Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment															
Carbon	C %	0.040 max.	Solution Annealing															
Silicon	Si %	1.000 max.																
Manganese	Mn %	1.000 max.																
Phosphorus	P %	0.040 max.																
Sulphur	S %	0.040 max.																
Chromium	Cr %	24.500 - 26.500																
Nickel	Ni %	4.700 - 6.000																
Molybdenum	Mo %	1.700 - 2.300																
Copper	Cu %	2.700 - 3.300																
Nitrogen	N %	0.100 - 0.250																
Iron	Fe %	Balance	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>690 min.</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>485 min.</td> </tr> <tr> <td>Elongation in %</td> <td>16 min.</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in BHN</td> <td>-</td> </tr> <tr> <td>Impact in Joule</td> <td>-</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	690 min.	Yield Strength in Mpa	485 min.	Elongation in %	16 min.	Reduction of Area in %	-	Hardness in BHN	-	Impact in Joule	-
Mechanical Properties																		
Tensile Strength in Mpa	690 min.																	
Yield Strength in Mpa	485 min.																	
Elongation in %	16 min.																	
Reduction of Area in %	-																	
Hardness in BHN	-																	
Impact in Joule	-																	
-	-	-																
-	-	-																
-	-	-																
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A995 1B	ASTM	USA	Casting
J93372	UNS	USA	Casting
A240 S32205	ASTM	USA	Plate, Sheet and Strip
A276 S32205	ASTM	USA	Bar and Shape
A988 S32205	ASTM	USA	Casting
J92205	UNS	USA	Casting
Z3CNUD26.5M	AFNOR NF	France	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com