

# Material - ASTM A890 CD6MN

## Standard Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Group-Ferrous Stainless Steel Alloys

Sub Group - ASTM A890 / A890M Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P%	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr%	24.000- 27.000		
Nickel	Ni%	4.000 - 6.000		
Molybdenum	Mo %	1.750- 2.500		
Nitrogen	N%	0.150- 0.250		
Iron	Fe%	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa: 655 min. Yield Strength in Mpa: 450 min. Elongation in %: 25 min. Reduction of Area in %: - Hardness in BHN: - Impact in Joule: -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A9953A	ASTM	USA	Casting
J93371	UNS	USA	Casting
A240UNS 32900	ASTM	USA	Steel, Sheet, Plate and Strip
A240UNS S32950	UNS	USA	Steel, Sheet, Plate and Strip
25Cr5NiMoN	ASTM	USA	Casting
3A	ASTM	USA	Casting
A995CD6MN	ASTM	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)