

Material: ASTM A959 S 32050

Standard Specification for Specifying Harmonized Standard Grade Compositions for Stainless Steels

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 959 Specifying Harmonized Standard Grade Compositions for Stainless Steels

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Tubes for Superheater and Heat exchanger

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	22.000 - 24.000
Nickel	Ni %	20.000 - 23.000
Molybdenum	Mo %	6.000 - 6.8000
Copper	Cu %	0.400 max.
Nitrogen	N %	0.210 - 0.320
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	
Mechanical Properties	
Tensile Strength in Mpa	570 min.
Yield Strength in Mpa	280 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 S 32050	ASTM	USA	Plate, Sheet and Strip
A358 S 32050	ASTM	USA	Pipes
A213 S 32050	ASTM	USA	Tubes for Superheater and Heat exchanger
A249 S 32050	ASTM	USA	Tubes for Superheater and Heat exchanger
S 32050	UNS	USA	Plate, Sheets and , Strip
A743 CK35MN	ASTM	USA	Casting
STS 350	KS	Korea	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India