

Material: ASTM A995 5A

Standard Specification for Castings, Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A995 / A995M Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	4.000 - 5.000		
Nitrogen	N %	0.100 - 0.300		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 515 min. Elongation in % 18 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A890 5A	ASTM	USA	Casting
G X2CrNiMoN26-7-4	AFNOR NF	France	Casting
1.4469	EN	European Union	Casting
GX2CrNiMoN26-7-4	DIN	Germany	Casting
GX2CrNiMoN25-7-4	DIN	Germany	Casting
J93404	UNS	USA	Casting
1.4469	WN	Germany	Casting

Disclaimer: **All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.**

Customer Care: +91-99090 45075 Email: info@icastllp.com